

TECHNICAL INFORMATION

WESTCO OLEAMIDE

Acid Value (max)	3
Amide	98%
Appearance	Light cream colored pellets or beads
Color (Gardner '63, max)	4
Iodine Value (max)	90
Melting Point °C	70 – 76
Storage	At least 2 years

One major use of Westco Oleamide is as a slip agent in polyethylene films. It functions by migrating to the film surface in a microscopic coating which reduces the coefficient of friction.