

## TECHNICAL INFORMATION

### RUBBERMAKERS SULPHUR OIL BLENDED

<b>Purity, % wt, minimum</b>	<b>99.5</b>
<b>Ash, % wt, maximum</b>	<b>0.10</b>
<b>Acidity % H<sub>2</sub>S<sub>4</sub>, maximum</b>	<b>0.01</b>
<b>Heat Loss, % wt, maximum</b>	<b>0.15</b>
<b>Oil, % wt target and limits</b>	
<b>Light (Typical)</b>	<b>0.25</b>
<b>Medium</b>	<b>0.5 ± 0.15</b>
<b>Heavy</b>	<b>1.0 ± 0.25</b>

#### PHYSICAL

<b>Passing 80 Mesh, % wt.</b>	<b>100 minimum</b>
<b>Passing 100 Mesh, % wt.</b>	<b>99.5 to 100</b>
<b>Passing 200 Mesh, % wt.</b>	<b>90.0 to 100</b>

rev. 6-99