

TECHNICAL INFORMATION

WESTCO CP-70

CHLORINATED PARAFFIN RESIN

Appearance	White to light yellow powder
*Chlorine content, %	70±1
*Softening point, °C	95 min
*Thermo stability C 175°C,% HCl	0.2 max
*Drying loss, %	1.0 max
*Acidity (mg KOH/g)	0.10
*Sieve residue (20 mesh), %	0.02 max
Specific Gravity, typical	1.60

***Values reported on Certificate of Analysis**