

# TECHNICAL INFORMATION

## WESTCO CBS

(n-cyclohexyl -2- benzothiazole sulfenamide)

**Westco CBS is a delayed action accelerator suitable for natural rubber and synthetic rubber; produces vulcanizates with high modulus and high tensile strength.**

### Specifications

Appearance	Grey white to light yellow		
Form	Granular	Powder	Oiled powder
Initial Melt Point, °C.	*98 min	*98 min	*98 min
Final Melt Point, °C.	*99 min	*99 min	*99 min
Moisture, %	*.5 max	*.5 max	*.5 max
Ash content, %	*.5 max	*.5 max	*.5 max
Sieve residue (100 Mesh),%	NA	*0.1 max	*0.1 max
Sulfenamide, %	96 min	96 min	96 min
Total sulfur, %	*23-24.7	*23-24.7	*23-24.7
Content of oil, %	NA	NA	*1-2
Free amines (Cyclohexylamine), %	*0.5 max	*0.5 max	*0.5 max
Grain strength	*2-4	NA	NA
Alcohol Insolubles, %	0.5 max	0.5 max	0.5 max
Specific Gravity, typical	1.29	1.29	1.29

\* Actual data will be reported on Certificate of Analysis

9/07