

TECHNICAL INFORMATION

DYPHENE 340

Heat-reactive phenolic resin

Appearance:	Amber flake
*Softening point, °C	80-95
*Methylol content, %	8-11
*Color	1-6
*S.G., typical	1.04

*Reported on C of A

Dyphene 340 is recommended for use in resin cured butyl rubber compounds.

Store in cool, dry location at 75°F or less.

Packaging: 50 lbs. net weight paper bags
375 lbs. net weight fiber drums

11/07