

TECHNICAL INFORMATION

WESTCO HRT/A RESINS

C₅/C₉ Hydrocarbon Resins

	*Softening point °C
HRT/A 80	80-90
HRT/A 90	90-100
HRT/A 95	95-105
HRT/A 100	100-110
HRT/A 110	110-120
HRT/A 120	120-130
HRT/A 130	130-140

All HRT/A resins conform to the following specifications:

*Color, 50% in toluene	10 max
*Acid number	0.5 max
*Ash, %	0.1 max
Iodine Value	70 – 140 (typical 120)
Flash point	280°C typical

***Values reported on Certificate of Analysis.**