

TECHNICAL INFORMATION

P – 3000

ZINC STEARATE POWDER

SPECIFICATIONS:

*Ash, %	13 - 14.5
*Free Fatty Acids, %	1.0 max
*Moisture, %	.5 max
Melting Point, °C	120 - 130
*Fineness, % through 325 mesh	95 min
Specific Gravity	1.09
Appearance:	Free Flowing White Powder

APPLICATIONS:

Coatings – P-3000 offers uniform and efficient flatting to solvent based paints, varnishes, and lacquers. P-3000 also provides particle release properties to abrasive coatings.

Rubber Processing – P-3000 provides excellent lubrication in mixing and excellent anti-tack or anti-blocking properties when used as a dust on uncured slabs and extruders.

Plastics Processing – P-3000 offers excellent lubrication in processing of polyolefin, polystyrene, polyvinyl chloride, and melamine formaldehyde polymers. In PVC, P-3000 offers the additional properties of providing benefits of heat stabilization and blowing agent activation.

8/05 D