

## TECHNICAL INFORMATION

### **PETRAC 270**

Low I.V.  
Stearic acid

**Petrac 270 can be used as an activator, dispersing agent, plasticizer and lubricant in rubber compound processing as well as an external lubricant and viscosity depressant in PVC processing.**

<b>*Acid Value</b>	<b>200 min</b>
<b>*Iodine Value</b>	<b>2 max</b>
<b>Unsaponifiable, %</b>	<b>1 max</b>
<b>*Titer, Degrees C</b>	<b>54 - 62</b>
<b>*Moisture, %</b>	<b>0.5 max</b>

**\*Actual Data will be reported on Certificate of Analysis.**

8/05