

TECHNICAL INFORMATION

WESTCO RC 510

Rutile Titanium Dioxide Chloride Process Surface treated with Al and Zr

Specifications

*TiO ₂ assay	92% min
*Whiteness	100% min
*Tinting Strength	100% min
*Volatile matter @105°C	0.8% max
*Resistivity of Water extract, %	80% min
*pH	6.5-8.5
*Oil Absorption, g/100g	20 max
*Rutile Content	97% min
Specific Gravity, typical	4.2

*Actual data will be reported on Certificate of Analysis

3/06