

# TECHNICAL INFORMATION

## WESTCO TiO<sub>2</sub> RUTILE SULFATE

### SPECIFICATIONS

<b>*TiO<sub>2</sub>, %</b>	<b>95 Min</b>
<b>Rutile Form, % total of TiO<sub>2</sub></b>	<b>95 Min</b>
<b>*Volatiles at 105°C, %</b>	<b>0.8 Max</b>
<b>*pH</b>	<b>6.5 - 9.0</b>
<b>*Oil absorption</b>	<b>19g/100g Max</b>
<b>*Residue on number 0045 sieve</b>	<b>0.10 Max</b>
<b>*Lightening Power, % Standard</b>	<b>94 Min</b>
<b>Specific Resistance, Ωm</b>	<b>60 Min</b>
<b>Specific Gravity, Typical</b>	<b>3.8</b>

**\*Actual data will be reported on Certificate of Analysis**

**3/06 R**