

**WESTCO™ BZ g (ZDBC) Accelerator
Zinc Dibutyldithiocarbamate
CAS# 136-23-2**

Technical Data:

WESTCO™ BZ g is a rubber accelerator for natural and synthetic rubber and latex. Provides fast cures at low temperatures; slower cure rates than with EZ (ZDEC) or MZ (ZDMC). Can be used up to 1.50 PHR without bloom.

Specification:

Form	Granule
Specifications	Limit
*Initial melt point	103°C Min.
*Zinc content	13 – 15%
*Moisture Content	0.4% Max.
*Grain Strength	0.5-2.5%

***Actual data will be reported on Certificate of Analysis**

Revised 9/2016

The technical information and suggestions for use contained herein are believed to be reliable, but they are not to be construed as warranties and no patent liability can be assumed.