

**WESTCO™ CI-25 DLD Coumarone Indene Resin
CAS# 63393-89-5**

72% CI 25 on an inert carrier

Technical Data:

WESTCO™ CI-25 DLD is used to provide tack to uncured natural or synthetic rubber compounds. It also functions as a plasticizer and softening agent. Typical loading levels would be 5.0 -15.0 phr.

Specifications:

Appearance	Tan free flowing powder
*CI 25 content	69-75%
Carrier	25-31%

***Reported on certificate of analysis**

Packaging: 50 lb. Bag

Revised 01/2016

The technical information and suggestions for use contained herein are believed to be reliable, but they are not to be construed as warranties and no patent liability can be assumed.